

## F694TX 極超微粒鎢鋼塗層深溝立銑刀

## End Mills For Rib Processing

**SMG**  
Carbide

**AlTiSiN**  
TX



## Type of Operation



## Work Material

P	H	M	K	N	S
●	●	●	○	○	○

**P** 鋼鐵  
Steel

**H** 硬化鋼 <38HRC  
Hardened Steel

**H** 硬化鋼 <48HRC  
Hardened Steel

**H** 硬化鋼 <56HRC  
Hardened Steel

**H** 硬化鋼 <68HRC  
Hardened Steel

**K** 鑄鐵  
Cast Iron

**N** 銅  
Copper

## Feature of product:

4刃平頭深溝立銑刀

廣泛用於精微模具、深溝清角。

搭配奈米多層膜塗層具有優異的潤滑及耐磨性。

可用於各式鋼鐵材料及電極銅。



Code No. F694TX-Dc×Li


Dc 0 -0.02	Li mm	Lc mm	L mm	d h5	D1 mm	AlTiSiN F694TX
1	3	1.5	50	4	0.95	●
1	4	1.5	50	4	0.95	●
1	6	1.5	50	4	0.95	●
1	8	1.5	50	4	0.95	●
1	10	1.5	50	4	0.95	●
1	12	1.5	50	4	0.95	●
1.5	4	2.3	50	4	1.45	●
1.5	6	2.3	50	4	1.45	●
1.5	8	2.3	50	4	1.45	●
1.5	10	2.3	50	4	1.45	●
1.5	12	2.3	50	4	1.45	●
1.5	16	2.3	50	4	1.45	●
2	6	3	50	4	1.95	●
2	8	3	50	4	1.95	●
2	10	3	50	4	1.95	●
2	12	3	50	4	1.95	●
2	16	3	50	4	1.95	●
2	20	3	60	4	1.95	●
2	25	3	60	4	1.95	●
2	30	3	70	4	1.95	●
3	8	4.5	50	6	2.85	●
3	10	4.5	50	6	2.85	●
3	12	4.5	50	6	2.85	●
3	16	4.5	60	6	2.85	●
3	20	4.5	60	6	2.85	●
3	25	4.5	70	6	2.85	●
3	30	4.5	70	6	2.85	●
4	12	6	60	6	3.85	●
4	16	6	60	6	3.85	●
4	20	6	70	6	3.85	●
4	25	6	70	6	3.85	●
4	30	6	80	6	3.85	●
4	40	6	90	6	3.85	●
5	16	7.5	60	6	4.85	●
5	20	7.5	70	6	4.85	●
5	30	7.5	80	6	4.85	●
5	40	7.5	90	6	4.85	●
6	20	9	70	6	5.85	●
6	30	9	80	6	5.85	●
6	40	9	90	6	5.85	●
6	50	9	100	6	5.85	●

## F694TX 切削條件參考表

## Recommended Milling Conditions

## Side Milling 側面切削

被削材 Work Material		GR.5 硬化鋼 Hardened Steel (38-48HRC)				GR.6 硬化鋼 Hardened Steel (48-56HRC)				GR.7 硬化鋼 Hardened Steel (56-68HRC)			
型號 Code No.	刃徑 × 頸長 Dc × L1	RPM 迴轉速度 (min-1)	Feed 進給速度 (mm/min)	ap (mm)	ae (mm)	RPM 迴轉速度 (min-1)	Feed 進給速度 (mm/min)	ap (mm)	ae (mm)	RPM 迴轉速度 (min-1)	Feed 進給速度 (mm/min)	ap (mm)	ae (mm)
F694TX	1×3	14,000	1,350	0.04	0.3	13,000	1,100	0.035	0.25	8,800	700	0.02	0.25
F694TX	1×4	13,800	1,310	0.039	0.270	12,000	1,070	0.031	0.243	8,500	640	0.015	0.243
F694TX	1×6	11,300	1,040	0.021	0.216	9,800	860	0.016	0.209	7,000	510	0.01	0.108
F694TX	1×8	9,800	780	0.02	0.189	8,500	720	0.012	0.16	6,100	420	0.008	0.094
F694TX	1×10	8,800	510	0.011	0.126	7,600	510	0.009	0.1	5,400	350	0.006	0.05
F694TX	1×12	8,300	490	0.01	0.1	7,200	490	0.005	0.1	5,000	300	0.003	0.05
F694TX	1.5×4	12,000	1,300	0.045	0.5	12,000	1,250	0.045	0.5	9,000	500	0.03	0.25
F694TX	1.5×6	11,600	1,280	0.041	0.486	10,600	1,210	0.038	0.445	8,100	460	0.025	0.202
F694TX	1.5×8	10,200	1,080	0.038	0.35	9,300	1,020	0.031	0.346	7,100	390	0.015	0.157
F694TX	1.5×10	9,000	900	0.03	0.3	8,200	800	0.03	0.3	6,500	360	0.01	0.1
F694TX	1.5×12	8,500	830	0.029	0.324	7,800	780	0.026	0.297	5,900	300	0.01	0.162
F694TX	1.5×16	7,400	670	0.018	0.216	6,800	600	0.014	0.198	5,100	230	0.005	0.108
F694TX	2×6	12,800	1,280	0.064	0.648	12,000	1,200	0.06	0.729	9,700	700	0.028	0.324
F694TX	2×8	11,200	1,160	0.058	0.612	10,400	1,100	0.055	0.648	8,400	600	0.026	0.288
F694TX	2×10	10,000	1,100	0.045	0.5	9,000	1,000	0.045	0.5	8,200	500	0.02	0.25
F694TX	2×12	9,100	1,030	0.046	0.405	8,500	960	0.044	0.405	6,900	420	0.018	0.180
F694TX	2×16	7,800	860	0.042	0.283	7,300	700	0.039	0.315	5,900	270	0.016	0.157
F694TX	2×20	7,000	800	0.025	0.198	6,600	650	0.024	0.198	5,300	290	0.007	0.116
F694TX	2×25	6,500	650	0.02	0.15	6,500	600	0.02	0.15	5,000	200	0.005	0.08
F694TX	2×30	6,000	500	0.02	0.1	6,000	450	0.02	0.1	4,500	150	0.003	0.05
F694TX	3×8	11,250	2,300	0.1	0.65	11,000	2,000	0.08	0.65	9,000	750	0.05	0.5
F694TX	3×10	11,250	2,277	0.0945	0.63	10,620	1,980	0.063	0.63	8,910	729	0.0423	0.45
F694TX	3×12	10,500	2,020	0.084	0.670	10,000	1,950	0.052	0.67	8,100	660	0.037	0.5
F694TX	3×16	9,200	1,680	0.064	0.634	8,800	1,600	0.04	0.63	7,100	570	0.027	0.378
F694TX	3×20	8,400	1,540	0.058	0.580	7,900	1,490	0.036	0.58	6,300	550	0.022	0.319
F694TX	3×25	7,500	1,350	0.05	0.4	7,000	1,100	0.025	0.4	6,000	450	0.01	0.2
F694TX	3×30	7,000	1,260	0.04	0.38	6,500	1,230	0.015	0.38	5,400	390	0.007	0.144
F694TX	4×12	8,500	1,400	0.1	1.0	7,100	1,350	0.078	1.08	6,000	760	0.051	0.76
F694TX	4×16	7,900	1,370	0.091	1.0	6,600	1,330	0.071	1.0	5,600	740	0.043	0.7
F694TX	4×20	6,200	1,200	0.06	0.8	5,200	1,120	0.047	0.8	4,500	630	0.022	0.56
F694TX	4×25	6,200	1,200	0.06	0.8	5,200	1,120	0.047	0.8	4,500	630	0.022	0.56
F694TX	4×30	5,500	960	0.037	0.648	4,600	920	0.029	0.648	3,900	600	0.011	0.388
F694TX	4×40	5,000	800	0.03	0.5	4,300	800	0.025	0.5	3,500	500	0.005	0.3
F694TX	5×16	8,000	1,100	0.15	1.0	8,000	1,100	0.15	1.0	5,500	700	0.05	0.6
F694TX	5×20	7,500	900	0.1	1.0	7,500	900	0.1	1.0	5,200	680	0.03	0.5
F694TX	5×30	6,500	700	0.08	0.5	6,500	700	0.08	0.5	4,800	630	0.02	0.3
F694TX	5×40	5,500	600	0.05	0.3	5,500	600	0.05	0.3	4,500	600	0.01	0.2
F694TX	6×20	7,000	1,000	0.3	1.2	7,000	1,000	0.3	1.2	5,000	650	0.05	0.6
F694TX	6×30	6,500	800	0.2	1.0	6,500	800	0.2	1.0	4,700	620	0.03	0.5
F694TX	6×40	6,000	700	0.15	0.8	6,000	700	0.15	0.8	4,400	580	0.02	0.3
F694TX	6×50	5,500	600	0.1	0.6	5,500	600	0.1	0.6	4,100	550	0.01	0.2



1. Please work with good rigidity / high precision facilities and collet chuck.
2. Please choose proper cutting fluid.
3. The cutting data is reference value only. Please adjust it according to your real working conditions.
4. If RPM is lower the reference value, the Feed rate (fz) and RPM should be reduced by the same proportion.
5. If vibration occurs during cutting, please reduce cutting parameter.

1. 請使用剛性好、精度高的設備和夾具。
2. 請選擇適用於工件材料的切削液。
3. 此切削條件表中的數值為切削條件的基準值，實際加工時，請考慮加工形狀、目的、使用機台等因素，對切削條件進行調整。
4. 如果機台轉速低於表中所列數值，則進給速度應與轉速按同一比例降低。
5. 切削加工時如果發生振顫，請降低切削條件。